

## Starting point formulation – Water-based pigment concentrates for universal application with DISPERBYK-2061

				Pigment		Pigment		Pigment		Pigment	
				Hansa Brilliant Yellow 2GX 70 Heubach	Novoperm Yellow HR 70 Heubach	Paliotol Yellow L 0962 HD BASF	Sico Orange L 3052 HD BASF	Novoperm Orange HL 70 Heubach	Paliotol Orange L 2930 HD BASF	Permanent Red FGR 70 Heubach	
				Supplier							
Position	Component	Supplier	Function	PY 74	PY 83	PY 138	PO 5	PO 36	PO 67	PR 112	
1	Water		Solvent	37.50	39.50	32.00	27.20	33.00	34.00	43.00	
2	Preservative		Preservative	0.10	0.10	0.10	0.10	0.10	0.10	0.10	
3	BYK-1640	BYK	Defoamer	0.50	0.50	0.40	0.40	0.40	0.40	0.50	
4	DISPERBYK-2061	BYK	Wetting and dispersing	4.00	4.00	10.00	7.50	7.00	7.00	5.30	
5	Blanc Fixe micro	Venator	Filler	10.00	-	-	-	-	-	10.00	
6	Pigment	See headline	Color	40.00	40.00	40.00	50.00	35.00	35.00	35.00	
7	BYK-1640	BYK	Defoamer	0.20	0.20	0.20	0.20	0.20	0.20	0.20	
8	Water		Solvent	7.70	15.70	17.30	14.60	24.30	23.30	5.90	
<b>Total</b>				<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	

### Instructions

Premix position 1–4, add pigment/filler and disperse well (beads are recommended), add position 7–8 while stirring.

### Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2061	10.00 %	10.00 %	25.00 %	15.00 %	20.00 %	20.00 %	15.10 %
----------------	---------	---------	---------	---------	---------	---------	---------

## Starting point formulation – Water-based pigment concentrates for universal application with DISPERBYK-2061

				Pigment	Irgazin Red L 3670 HD BASF	Hostaperm Pink E Heubach	Sudaperm Pink 2997 Sudarshan	Quindo Violet 19 Sun Chemical	Sunfast Blue 248-0615 Sun Chemical	Heliogen Blue L 7101 F	Heliogen Green L 8730
Position	Component	Supplier	Function	PR 254	PR 122	PR 122	PV 19	PB 15:2	PB 15:4	PG 7	
1	Water		Solvent	35.00	60.00	62.00	29.50	30.00	37.00	35.00	
2	Preservative		Preservative	0.10	0.10	0.10	0.10	0.10	0.10	0.10	
3	BYK-1640	BYK	Defoamer	0.50	0.70	0.70	0.40	0.50	0.50	0.50	
4	DISPERBYK-2061	BYK	Wetting and dispersing	5.30	4.00	4.00	7.50	12.30	8.80	6.00	
5	Blanc Fixe micro	Venator	Filler	10.00	-	-	10.00	-	10.00	10.00	
6	Pigment	See headline	Color	35.00	20.00	20.00	25.00	35.00	35.00	40.00	
7	BYK-1640	BYK	Defoamer	0.20	0.20	0.20	0.20	0.20	0.20	0.20	
8	Water		Solvent	13.90	15.00	13.00	27.30	21.90	8.40	8.20	
<b>Total</b>				<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	

### Instructions

Premix position 1–4, add pigment/filler and disperse well (beads are recommended), add position 7–8 while stirring.

### Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2061	15.10 %	20.00 %	20.00 %	30.00 %	35.10 %	25.10 %	15.00 %
----------------	---------	---------	---------	---------	---------	---------	---------

## Starting point formulation – Water-based pigment concentrates for universal application with DISPERBYK-2061

Position	Component	Supplier	Function	Pigment			
				Elftex 415 Cabot Corporation	Raven 410 Birla Carbon	Lamp Black 101 Orion Engineered Carbons	Monarch 120 Cabot Corporation
				PBk 7	PBk 7	PBk 7	PBk 7
1	Water		Solvent	24.00	24.00	48.00	39.50
2	Preservative		Preservative	0.10	0.10	0.10	0.10
3	BYK-1640	BYK	Defoamer	0.40	0.40	0.50	0.40
4	DISPERBYK-2061	BYK	Wetting and dispersing	6.00	6.00	8.00	9.60
5	Blanc Fixe micro	Venator	Filler	-	-	15.00	-
6	Pigment	See headline	Color	20.00	20.00	20.00	32.00
7	BYK-1640	BYK	Defoamer	0.10	0.10	0.20	0.10
8	Water		Solvent	49.40	49.40	8.20	18.30
<b>Total</b>				<b>100.00</b>	<b>100.00</b>	<b>100.00</b>	<b>100.00</b>

### Instructions

Premix position 1–4, add pigment/filler and disperse well (beads are recommended), add position 7–8 while stirring.

### Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2061	30.00 %	30.00 %	40.00 %	30.00 %
----------------	---------	---------	---------	---------

**BYK-Chemie GmbH**  
Abelstraße 45  
46483 Wesel  
Germany  
Tel +49 281 670-0  
Fax +49 281 65735

[info@byk.com](mailto:info@byk.com)  
[www.byk.com](http://www.byk.com)

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKOZBLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAC®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.

