

Starting point formulation – Pigment concentrates for solvent-borne floor coatings with DISPERBYK-2152 TF

				Pigment		Supplier			
				Kronos 2190 Kronos International	Bayferrox 3920 Lanxess	Hostaperm Yellow H4G Heubach	Novoperm Orange HL 70 Heubach	Bayferrox 120 M Lanxess	Novoperm Red F3RK 70 Heubach
Position	Component	Supplier	Function	PW 6	PY 42	PY 154	PO 36	PR 101	PR 170
1	Epikote 1001 (75 % in xylene)	Hexion	Resin	17.80	18.30	16.00	16.00	17.80	20.00
2	MPA		Solvent	19.90	21.80	45.60	47.40	16.60	41.75
3	PM		Solvent	-	-	-	-	-	-
4	DISPERBYK-2152 TF	BYK	Wetting and dispersing	1.50	4.10	8.10	6.00	4.80	7.50
5	BYK-SYNERGIST 2100	BYK	Wetting and dispersing	-	-	-	-	-	-
6	BYK-SYNERGIST 2105	BYK	Wetting and dispersing	-	-	-	0.60	-	0.75
7	RHEOBYK-7410 ET	BYK	Anti-settling	0.80	0.80	0.30	-	0.80	-
8	Pigment	See headline	Color	60.00	55.00	30.00	30.00	60.00	30.00
Total				100.00	100.00	100.00	100.00	100.00	100.00

Instructions

Premix position 1–6, add position 7 while stirring, add pigment and disperse well (dissolver and beads are recommended).

Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2152 TF	2.50 %	7.50 %	27.00 %	20.00 %	8.00 %	25.00 %
BYK-SYNERGIST 2100	-	-	-	-	-	-
BYK-SYNERGIST 2105	-	-	-	2.00 %	-	2.50 %

Starting point formulation – Pigment concentrates for solvent-borne floor coatings with DISPERBYK-2152 TF

Position	Component	Supplier	Function	Pigment	Hostaperm	Hostaperm	Heliogen	Heliogen	Special
				Supplier	Pink E Heubach	Violet RL-NF Heubach	Blue L 7101 F BASF	Green L 8735 BASF	Black 4 Orion Engineered Carbons
				PR 122	PV 23	PB 15:4	PG 7	PB 9	
1	Epikote 1001 (75 % in xylene)	Hexion	Resin	17.80	18.30	16.00	16.00	17.80	
2	MPA		Solvent	19.90	21.80	45.60	47.40	16.60	
3	PM		Solvent	-	-	-	-	-	
4	DISPERBYK-2152 TF	BYK	Wetting and dispersing	1.50	4.10	8.10	6.00	4.80	
5	BYK-SYNERGIST 2100	BYK	Wetting and dispersing	-	-	-	-	-	
6	BYK-SYNERGIST 2105	BYK	Wetting and dispersing	-	-	-	0.60	-	
7	RHEOBYK-7410 ET	BYK	Anti-settling	0.80	0.80	0.30	-	0.80	
8	Pigment	See headline	Color	60.00	55.00	30.00	30.00	60.00	
Total				100.00	100.00	100.00	100.00	100.00	

Instructions

Premix position 1–6, add position 7 while stirring, add pigment and disperse well (dissolver and beads are recommended).

Characteristic data

Additive dosage (solids on pigment)

DISPERBYK-2152 TF	28.00 %	38.00 %	35.00 %	35.00 %	35.00 %
BYK-SYNERGIST 2100	-	-	-	5.00 %	-
BYK-SYNERGIST 2105	-	-	-	-	-

BYK-Chemie GmbH
Abelstraße 45
46483 Wesel
Germany
Tel +49 281 670-0
Fax +49 281 65735

info@byk.com
www.byk.com

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK-AQUAGEL®, BYK-DYNWET®, BYK-MAX®, BYK-SILCLEAN®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKOZBLOCK®, BYKONITE®, BYKOPLAST®, BYKUMEN®, CARBOBYK®, CERACOL®, CERAFAK®, CERAFLOUR®, CERAMAT®, CERATIX®, CLAYTONE®, CLOISITE®, DISPERBYK®, DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIFLO®, OPTIGEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOBYK®, RECYCLOSSORB®, RECYCLOSTAB®, RHEOBYK®, RHEOCIN®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.

The information herein is based on our present knowledge and experience. The information merely describes the properties of our products but no guarantee of properties in the legal sense shall be implied. We recommend testing our products as to their suitability for your envisaged purpose prior to use. No warranties of any kind, either express or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding any products mentioned herein and data or information set forth, or that such products, data or information may be used without infringing intellectual property rights of third parties. We reserve the right to make any changes according to technological progress or further developments.

This issue replaces all previous versions.

