

Starting point formulation – Water-based perfume gel


Surfactant-free perfume gel based on pickering emulsion – utilizing LAPONITE-RD

Formulation

Position	Component	Supplier	Function	Weight (g)
1	Demineralized water		Solvent	82.60
2	LAPONITE-RD	вук	Thickener	2.40
3	Pickering emulsion		Perfume	15.00
Total				100.00

Instructions

- Mix water with LAPONITE RD at 1000–1500 rpm for 15 min.
- Add pickering emulsion with low speed.



Characteristic data/specification

Data	Unit	Value
LAPONITE content	<u></u> %	2.58
Perfume oil content	%	3.00
Ratio oil : LAPONITE		100.00 : 86.00

Further information/application


• The oil emulsion is designed to be used as it is.

contact

BYK-Chemie GmbH Abelstraße 45 46483 Wesel Germany Tel +49 281 670-0

Fax +49 281 65735

ADD-MAX®, ADD-VANCE®, ANTI-TERRA®, AQUACER®, AQUAMAT®, AQUATIX®, BENTOLITE®, BYK®, BYK®-AQUAGEL®, BYK®-DYNWET®, BYK®-SILCLEAN®, BYKANOL®, BYKANOL®, BYKCARE®, BYKETOL®, BYKJET®, BYKOZBLOCK®, BYKONITE®, BYKOPIAST®, BYKUMEN®, CARBOBYK®, CERAFOL®, CERAFLOUR®, CERA DISPERPLAST®, FULACOLOR®, FULCAT®, GARAMITE®, GELWHITE®, HORDAMER®, LACTIMON®, LAPONITE®, MINERPOL®, NANOBYK®, OPTIBENT®, OPTIBEL®, POLYAD®, PRIEX®, PURABYK®, PURE THIX®, RECYCLOBLEND®, RECYCLOSTAB®, RECYCLOSTAB®, RHEODIX®, RHEOTIX®, SCONA®, SILBYK®, TIXOGEL® and VISCOBYK® are registered trademarks of the BYK group.



This issue replaces all previous versions.



